

TEST REPORT

Number : HGHT05834062

Applicant : SHAOXING IDEAL TEXTILE CLOTHING CO., LTD
RM2102, NO.1 FUSHEN MANSION, DIDANG NEW
CITY, SHAOXING CITY, ZHEJIANG PROVINCE,
CHINA
Attn : LI MING

Date : Dec 14, 2018

Sample Description As Declared :


No. Of Sample : One (1)
Fibre Content : 100% Polyester
Material : Knitted Fabric
Finishing : -
End Uses : Upholstery
Colour : Blue
Style No. : PIRAMIDE
Order No./PO No. : -
Buyer's Name : -
Manufacturer's Name : -
Ref. : -

Applicant's Provided Care Instruction/Label :

-

Date Received/Date Test Started : Dec 03, 2018

Prepared And Checked By:
For Intertek Testing Services Ltd., Hangzhou



Vivian Zhao
Manager



Intertek Testing Services Ltd., Shanghai , Hangzhou Branch

2-4F, Building No.6, Hangzhou Huaye High-Tech
Park, 1180 Bin'an Road, Hangzhou 310052, China

上海天祥质量技术服务有限公司杭州分公司

中国杭州滨安路 1180 号杭州华业高科技园 6 号楼 2-4 楼 邮编:310052

Tel: +86 571 8768 8218 Fax: +86 571 8679 0296 E-mail: hztml@intertek.com Website: Intertek.com

Attention is drawn to the terms and conditions printed overleaf

TEST REPORT

Number : HGHT05834062

Conclusion:


Color Fastness To Crocking	M
Color Fastness To Light	#
Snagging Resistance	M
Bursting Strength As Received	M
Pilling Resistance As Received	#
Abrasion Resistance	#

Note : M = Commercially Acceptable
N/A = Not Applicable

F = Fail

= No Comment

Prepared And Checked By:
For Intertek Testing Services Ltd., Hangzhou



Vivian Zhao
Manager



TEST REPORT

Number : HGHT05834062

Tests Conducted (As Requested By The Applicant)

1 Color Fastness To Crocking (AATCC 8-2016):

Dry	4.5
Wet	4.5

2 Color Fastness To Light (AATCC 16.3-2014, Option 3, Xenon-Arc Lamp):

<u>40 AATCC Fading Unit (AFU) Exposure</u> Grade	4
---	---

3 Snagging Resistance (ASTM D3939/D3939M-2013 (R2017), 600 Revolutions Test In ICI Mace Snag Tester):

<u>Along Wales</u> Rating	4
------------------------------	---

<u>Along Courses</u> Rating	4
--------------------------------	---

Overall Average Rating	4
------------------------	---

Remark: Visual Rating Standards: ICI Photographic Snagging Standards.

4 Bursting Strength As Received (ASTM D3786/D3786M-18, Mullen Type Burster):

Over 80.0 lbf/in²

5 Pilling Resistance As Received (ASTM D3512/D3512M-10 (2014), Random Tumbler):

<u>After A 30-Minute Test</u> Rating	4
---	---

Remark : Viewing Option - ASTM Lightbox

TEST REPORT

Number : HGHT05834062

Tests Conducted (As Requested By The Applicant)

- 6 Abrasion Resistance (ASTM D4966-12(2016), Option 1, Martindale Abrasion And Pilling Tester, 9 kPa Total Pressure):

Resistance
Face Side

Over 60,000 Rubs

End of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

This report shall not be reproduced except in full, without written approval of the laboratory.